

# Tradies Choice - FAST SET

C2SIFTI:

15 YEAR

20kg

# TRADIES CHOICE FASTSET



#### DESCRIPTION

Tradies Choice Fastset is a white polymer modified, fast setting, cement-based tile adhesive designed for internal and external applications. Can be used for ceramic, porcelain and vitrified tiles. Tradies Choice Fastset is suitable for some Class A moisture sensitive tiles. For class B and C please contact the SAS Technical Team. Fast set dries in 3 hours.



## CLASSIFICATION

C2 Improved adhesion

- S1 Flexible
- F Fast setting
- T Non slump
- E Extended open time

#### SUBSTRATES

Concrete render, rendered brick work, plaster board, fibre cement, SAS approved waterproofing membranes.



#### **SURFACE PREPARATION**

The surface must be clean, dry, firm and free of dust oil, grease, wax and curing compounds. The substrate must be installed according to the relevant standards and manufacturer recommendations. All porous surfaces must be primed with SAS Master Primer. For non-porous surfaces such as existing tiles, adhesives must be primed using SAS Master Primer neat. Please contact SAS Technical Team for further information.



#### MIXING

Mix 6 litres of water to 20kg of Tradies Choice Fastset. Mix with a mixing paddle until a creamy consistency is achieved, and powder is free of lumps. Allow mixture to stand for 3 minutes, remix, then use the adhesive.



## **FIXING**

Tiles should be fixed in accordance with Australia Standard AS 3958. Apply the adhesive using a notched trowel. For tiles up to 300 x 300mm use a 10mm notch and for greater than 400 x 400mm use a 12mm notch and butter the back of each tile. Apply only up to  $1\text{m}^2$  at a time. Press the tiles firmly into the adhesive before it skins. Do not spot fix, remove all excess adhesive from the tiles before it sets. For information that is not listed please contact the SAS technical team.



# MOVEMENT JOINTS

Movement joints must be in accordance with Australian Standard AS 3958.



### **DRYING TIME**

Allow the adhesive to dry for at least 3 hours at 20°C. Note: do not tile in temperatures above 40°C or below 5°C.



### **GROUTING**

Grouting can commence 3 hours after tiling is completed using SAS range of grouts.



### COVERAGE

A 20kg bag of Tradies Choice Fastset will cover approximately 6m<sup>2</sup> using a 10mm notched trowel.



## **PACKAGING**



SAS Australasia Pty Ltd 1300 202 894 WWW.SaS-aa.com.au

ABN: 83 617 827 282



# Tradies Choice — FAST SET

## **Applying**

- Tiles should be fixed in accordance with the Australian Standards AS3958.1-2007.
- Ensure the back of each tile is clean free form dust and other contaminants.
- Apply the adhesive onto the substrate but do not exceed more than 1m2 at a time.
- When back buttering is required use the straight side of the trowel and apply a thin coating of adhesive onto the tile.
- When laying the tiles make sure you move the tile forward and back 90 degrees across the direction of the beads of adhesive leaving no voids under the tile. It is important to lift a tile every now and then to check that sufficient coverage is achieved 90-100%.
- All adhesive residue must be removed from the tile and joint while the adhesive is still wet.
- After the tile adhesive is completely cured grouting can begin using Tradies choice range of grouts.
- For all other applications not mentioned please contact the SAS Technical team.
- Note: Protect tiling from other trades and weather. Do not allow traffic until all the tiling and grouting is completed.

#### **Precautions**

- Tradies Choice Fast Set cannot be used for tiling over tongue and grooved timber flooring, particle board.
- Tradies Choice Fast Set cannot be used for tiling over solvent based waterproofing membranes.
- Tradies Choice Fast Set cannot be used for tiling in immersed situations such as swimming pools and spas etc.
- Do not use for tiling over existing tiles in immersed situations such as swimming pools spas etc.
- Tradies Choice Fast Set can be used for fixing moisture sensitive tiles or stone. (Class A) Please call SAS Technical Team for further information.
- When tiling externally that is above 2.7m high please contact the SAS Technical team for further information.

## **Technical Data**

- Open Time 30 min at 23° C
- Appearance White powder
- Slump No
- Time before grouting 3 hours
- Return to service dry 24 hours
- Return to wet service 2 days

SDS is available from www.sas-aa.com.au





SAS Australasia Pty Ltd 1300 202 894 WWW.SaS-aa.com.au

ABN: 83 617 827 282

Date:1.10.17